CASHMERE MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
Water absorption of the body	ISO 10545-3	≤ 0.5%	Conformity
Breaking strength	ISO 10545-4	≥ 35 N/mm^2	Conformity
Abrasion resistance	ISO 10545-7		PEI 4
Frost resistance	ISO 10545-12	No samples must show ruptures or noticable surface alteration	Conformity
Chemical resistance	ISO 10545-13	No samples must show visible signs of chemical attack	Conformity
Thermal shock resistance	ISO 10545-9		Conformity
Dynamic coefficient of friction	BOT 3000E	ANSI A137.1:2012	0.56
Slight Variation	See Below		V2

Uniform appearance
V1

Slight Variation
V2

Moderate Variation
V3

Substantial Variation
V4

FOR THE BEST PRODUCT LAYING RESULTS, MATERIAL FROM AT LEAST THREE BOXES SHOULD BE MIXED

ENERGIE KER

www.bfceramics.com

2005 International Parkway Fredericksburg, VA 22406 I Phone: 540-286-3000 I Fax: 540-286-3010