

HEXAGONIA MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3		< 0.5%
 Breaking strength	ISO 10545-4		> 35 N/mm ²
 Abrasion resistance	ISO 10545-7	Determination of Resistance to Surface Abrasion for Glazed Tiles	PEI IV
 Frost resistance	ISO 10545-12	Frost Proof	Resistant
 Chemical resistance	ISO 10545-13	Resistant to Acid	GLA
 Thermal shock resistance	ISO 10545-5	The coefficient of linear thermal expansion is determined for the temperature range from ambient temperature to 100° C.	5.8x10 ⁻⁶ °C ⁻¹
 Dynamic coefficient of friction	BOT 3000E	ANSI A137.1: 2012	0.57
 Slight Variation	See Below		V2



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

CA
OPULENZA

www.bfceramics.com