

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	UNI EN ISO 10545-3	$\leq 0.5\%$	Conformity
 Breaking strength	UNI EN ISO 10545-4	$\geq 35 \text{ N/mm}^2$	Conformity
 Abrasion resistance	UNI EN ISO 10545-7		PEI 4
 Frost resistance	UNI EN ISO 10545-12	No samples must show ruptures or noticeable surface alteration	Conformity
 Chemical resistance	UNI EN ISO 10545-13	No samples must show visible signs of chemical attack	Conformity
 Thermal shock resistance	UNI EN ISO 10545-5		Conformity
 Dynamic coefficient of friction	BOT 3000E	ANSI A137.1:2012	0.63: Sintra 0.64: Maya 0.65: Almada, Porto 0.66: Tomar
 Slight Variation	See Below		V2



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

FOR THE BEST PRODUCT LAYING RESULTS, MATERIAL FROM AT LEAST THREE BOXES SHOULD BE MIXED



www.bfceramics.com