









# OLD TOWNE MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	$\leq 0.5\%$	$< 0.3\%$
 <b>Breaking strength</b>	ISO 10545-4	$R \geq 35\text{N/mm}^2$ $S > 700$ (spessore $< 7.5\text{mm}$ ) $S > 1300$ (spessore $\geq 7.5\text{mm}$ )	$> 46\text{N/mm}^2$
 <b>Abrasion resistance</b>	ISO 10545-7	Abrasion Class from I to V	Class IV - Total White Class V - All Other Colors
 <b>Frost resistance</b>	ISO 10545-12	Samples must not show alterations on the surface	OK
 <b>Chemical resistance</b>	ISO 10545-13	- Resistance to low/high concentrations of alkalis and acids - minimum Class B - Resistance to household chemical products and swimming pool additives minimum classification B	A•HA•LA
 <b>Thermal shock resistance</b>	ISO 10545-9		
 <b>Dynamic coefficient of friction</b>	BOT 3000E	DCOF ANSI A137.1:2012	0.55
 <b>Variation</b>	See Below		V1 - Total White V4 - Old Brown V3 - All Other Colors



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

*For the best product laying results, material from at least three boxes should be mixed.*

CERAMICHE  D'ARTE

[www.bfceramics.com](http://www.bfceramics.com)