

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ANSI/ISO-(%)	< 0.5%
 Breaking strength	ISO 10545-4	ANSI-(lbf) ISO-(N)	≥ 400 > 1750
 Abrasion resistance	ISO 10545-7	ANSI/ISO	Class 4
 Frost resistance	ISO 10545-12	ANSI/ISO	Pass
 Chemical resistance	ISO 10545-13	ANSI/ISO	Class A
 Thermal shock resistance	ISO 10545-5		
 Dynamic coefficient of friction	BOT 3000E	ANSI-DCOF (wet) ISO-R Value	Matte: 0.63 Matte R (-)
 Shade Variation	See Below		V3



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

