









QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	EN ISO 10545-3	E > 10%
 Breaking strength	ISO 10545-4	EN ISO 10545-4	E > 7.5 mm > 600 N E < 7.5 mm > 200 N
 Abrasion resistance	ISO 10545-7	PEI	1
 Frost resistance	ISO 10545-11	EN ISO 10545-11	Not Resistant
 Chemical resistance	ISO 10545-13	Resistance to Household Chemicals and Swimming Pool Salts Resistance to Low Concentrations Resistance to High Concentrations	Min GB GLA GHA
 Thermal shock resistance	ISO 10545-9	EN ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	Not Applicable - Wall Tile Only	
 Shade Variation	See Below		V1



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

Test values are based on ANSI/ISO standards according to: ANSI A137.1-Non-Vitreous P4 Class, ISO 13006-L Group; EN14411-L Group. Variances in test values can occur in different production lots.

Colorker®

www.bfceramics.com