

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	$\leq 0.5 \%$	0.6 %
 Breaking strength	ISO 10545-4	$\geq 35 \text{ N/mm}^2$ $\geq 1300 \text{ N}$ $\geq 700 \text{ N}$	32 Sp, Th, Ep, Dk $\geq 7.5\text{mm}$ Sp, Th, Ep, Dk $< 7.5\text{mm}$
 Abrasion resistance	ISO 10545-7		
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	ISO 10545-13	Min Class 3
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI DCOF A137.1-2012	0.62
 Shade Variation	See Below	Moderation Variation	V3



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

Warning: Storage up to maximum 3 stacked pallets for 24"x48" product.

EK
ENERGIE KER

www.bfceramics.com