

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	> 10%	Compliant
 Breaking strength	ISO 10545-4	≥ 15 N/mm ² ≥ 600 N	Compliant
 Abrasion resistance	ISO 10545-7	ISO 10545-7	Class 3: Ink, Niagra, Pine, Torrae Class 4: Blush, Dove, Sage Class 5: Ink
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Chemical Resistance: Declared Value Household Chemicals: B Min	LA-HB A
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	Not Applicable: Wall Tile Only	
 Shade Variation	See Below	Uniform Appearance	V1



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

CERAMICHE D'ARTE

www.bfceramics.com

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	> 10%	Compliant
 Breaking strength	ISO 10545-4	$\geq 15 \text{ N/mm}^2$ $\geq 600 \text{ N}$	Compliant
 Abrasion resistance	ISO 10545-7	ISO 10545-7	Class 3: Ink, Niagra, Pine, Torrae Class 4: Blush, Dove, Sage Class 5: Ink
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Chemical Resistance: Declared Value Household Chemicals: B Min	LA-HA A
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	Not Applicable: Wall Tile Only	
 Shade Variation	See Below	Uniform Appearance	V1



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

CERAMICHE  D'ARTE

www.bfceramics.com

DUST NATURAL (HEX)

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	$\leq 0.5\%$	Compliant
 Breaking strength	ISO 10545-4	≥ 1300 N	Compliant
 Abrasion resistance	ISO 10545-7	Declared class	PEI 4: Ice PEI 3: All Remaining Colors
 Frost resistance	ISO 10545-12	No alterations	Resistant
 Chemical resistance	ISO 10545-13	Declared Value B Min	LA-HA Resistant
 Thermal shock resistance	ISO 10545-9	No Alterations	Resistant
 Dynamic coefficient of friction	BOT 3000E	Tribometer BOT3000E cod. MCP C143	0.68
 Shade Variation	See Below	Uniform Appearance	V1



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

CERAMICHE D'ARTE

www.bfceramics.com